

### Product Design

Foam-LOK™ OC is an **open-cell** spray applied foam, which when installed following application guidelines adheres tenaciously to framing members and substrates. Foam-LOK™ OC **open-cell** provides superior energy economy and durability while significantly reducing unmanaged moisture and air infiltration.

### Product Use

Foam-LOK™ OC forms a completely sealed air barrier in wall cavities and can be used to fill 2" x 6" stud wall construction in a single application. Its performance is superior to commonly used fiberglass batt or board stock. It adheres well to most building materials and will provide a continuous barrier against air infiltration for the life of the building. As a component of a "systems approach to proper building envelope construction in both residential and commercial construction, Foam-LOK™ OC provides exceptional performance in reducing heat transfer, moisture gain and improving racking strength.

### Recommended Product Applications

- Walls
- Unvented Attics
- Ceilings
- Floors
- Vented Attics
- Unvented Crawl Spaces
- Vented Crawl Spaces

### Recommended Processing Parameters

|                                |                |
|--------------------------------|----------------|
| <b>Processing Designation:</b> | <b>Regular</b> |
| Ambient Temperature:           | 50-120°F       |

Optimum hose pressure and temperature may vary as a function of the type of equipment, ambient and substrate conditions, and the specific application. It is the responsibility of the applicator to properly interpret equipment technical literature, particularly information that relates acceptable combinations of gun chamber size, proportioner output, and material pressures.

|                                |                              |
|--------------------------------|------------------------------|
| <b>Processing Designation:</b> | <b>Foam-LOK OC</b>           |
| Equipment Dynamic Pressure:    | 1,100 - 1,500 psi            |
| Preheat Temperature            | 125 - 140° F<br>(52 - 60° C) |
| Hose Heat Temperature          | 125 - 140° F<br>(52 - 60° C) |
| Drum Temperature: Storage      | 65 - 85° F<br>(18 - 29° C)   |

**The shelf life will be 3 months when stored within recommended temperature range.**

2:1 transfer pumps are recommended for material transfer from container to the proportioner.

**CAUTION:** Extreme care must be taken when removing and reinstalling drum transfer pumps so as NOT to reverse the "A" and "B" components.

Do not configure equipment to recirculate Foam-LOK OC from proportioner back into drum. Do not recirculate or mix other suppliers' "A" or "B" component into Foam-LOK containers.

The plural component proportioner must be capable of supplying each component within ± 2% of the desired 1:1 mixing ratio by volume.

### Physical Properties

| Properties                                      | Test Method/ Requirements                              | Value          |
|---|--|----------------|
| Aged "R" Value:                                 | ASTM C-518   | 3.9 per inch   |
| Core Density:                                   | ASTM D-1622  | .4-.6 lbs./ft3 |
| Open Cell Content:                              | ASTM D-2856  | >94%           |
| Tensile Strength:                               | ASTM D-1623  | 3 psi          |
| Dimensional Stability: 28 days at 160°F, 100%RH | ASTM D-2126<br>15% max by volume change                | 3%             |
| Sound Transmission Coefficient                  | ASTM E-90-85/<br>E413<br>Sound Transmission Loss in dB | 41             |

### Credentials/Certifications

#### ICC ESR-2847

Foam-LOK OC is a **Class I** formulation, as Tested per ASTM E84, and possess the flammability characteristics shown:

| ASTM Method E84   | Class I | Class II | Class III |
|-------------------|---------|----------|-----------|
| Flame Spread      | ≤25     | ≤75      | Non Rated |
| Smoke Development | ≤450    | ≤450     | Non Rated |

The insulation at a maximum thickness of 6 inches (102 mm) and a nominal density of .5 pcf, has a flame-spread index of 25 or less and smoke-developed index of 450 or less when tested in accordance with ASTM E84.

# FOAM-LOK™

## SPRAY FOAM INSULATION

ENERGY SAVINGS FOR LIFE

# Foam-LOK OC

Open Cell Spray Foam Insulation FL500

Rev. Date: 04/23/09

Applicators should limit Foam-LOK OC thickness to 6 inches per pass for optimal processing and physical properties. Second passes if necessary should be applied after 10 minutes of cure time. If additional passes are needed, applicators should wait 30 minutes between passes for optimal foam processing.

### Thermal Barrier

IRC and IBC codes require that SPF be separated from the interior of a building by an approved fifteen (15) minute thermal barrier, such as 1/2" gypsum wall board or equivalent, installed per manufacturer's instructions and corresponding code requirements. There are exceptions to the thermal barrier requirement: (1) Code authorities may approve coverings based on fire tests specific to the SPF application. For example, covering systems that successfully pass large scale tests may be approved by code authorities in lieu of a thermal barrier; (2) SPF protected by 1" thick masonry does not need a thermal barrier. Certain materials that offer protection from ignition, called "ignition barriers," may not be considered as thermal barrier alternatives unless they comply with NFPA 286 or other similar full scale tests. Applicators should request test data and code body approvals or other written indications of acceptability under the code to be sure that the product selected offers code-compliant protection. Applicators should ensure the safety of the jobsite and construction personnel by posting appropriate signs warning that all "hot work" such as welding, soldering, and cutting with torches should take place no less than 35 feet from any exposed foam. If "hot work" must be performed all spray polyurethane foam should be covered with an appropriate fire or welder's blanket, and a fire watch should be provided.

### Handling and Safety

Respiratory protection is **MANDATORY!** Contact Lapolla Industries for a copy of the Model Respiratory Protection Program developed by API or visit their website at [www.polyurethane.org](http://www.polyurethane.org). Persons with known respiratory allergies should avoid exposure to the "A" component. The "A" component contains reactive isocyanate groups while the "B" component contains amine and/or catalysts. Both materials must be handled and used with adequate ventilation. The vapors must not exceed the TLV (0.02 parts per million) for isocyanates. Avoid breathing vapors. Wear a NIOSH approved respirator. If inhalation of vapors occur, remove victim from contaminated area and administer oxygen if breathing is difficult.

Call a physician immediately. Avoid contact with skin, eyes, and clothing. Open containers carefully, allowing any pressure to be relieved slowly and safely. Wear chemical safety goggles and rubber gloves when handling or working with these materials. In case of eye contact, immediately flush with large amounts of water for at least fifteen minutes. Consult a physician immediately. In case of skin contact, wash area with soap and water. Wash clothes before reuse.

### In Case of Spills or Leaks

#### Steps To Be Taken-

- Utilize appropriate personal protective equipment (PPE.)
- Contain and cover spilled material with a loose, absorbent material such as oil-dry, vermiculite, sawdust or Fuller's earth.
- Shovel absorbent waste material into proper waste containers
- Wash the contaminated areas thoroughly with hot, soapy water.
- Ventilate area to remove vapors.
- Report sizeable spills to proper environmental agencies.

### In Case of Fire

**Extinguishing Media-**Dry chemical extinguishers such as mono ammonium phosphate, potassium sulfate, and potassium chloride. Additionally, carbon dioxide, high expansion (proteinic) chemical foam, or water spray for large fires.

### DISCLAIMER

The data presented herein is not intended for use by nonprofessional applicators, or those persons who do not purchase or utilize this product in the normal course of their business. The potential user must perform any pertinent tests in order to determine the product's performance and suitability in the intended application, since final determination of fitness of the product for any particular use is the responsibility of the buyer.

All guarantees and warranties as to products supplied by Lapolla Industries shall have only those guarantees and warranties expressed in writing by the manufacturer. The buyer's sole remedy as to any material claims will be against the applicator of the product. The aforementioned data on this product is to be used as a guide and is subject to change without notice. The information herein is believed to be reliable, but unknown risks may be present. **NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING PATENT WARRANTIES OR WARRANTIES OF MERCHANTABILITY OR FITNESS FOR USE, ARE MADE BY LAPOLLA WITH RESPECT TO OUR PRODUCTS OR INFORMATION SET FORTH HEREIN.**

To the best of our knowledge, the technical data contained herein is true and accurate at the date of issuance and is subject to change without prior notice. User must contact Lapolla Industries, Inc. to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Lapolla Industries, Inc.'s quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of product. **NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY LAPOLLA INDUSTRIES, INC., EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.**

